



Brunswick Cellulose Brunswick, Georgia



Leaf River Cellulose New Augusta, Mississippi

GP Cellulose, LLC 133 Peachtree Street NE Atlanta, Georgia 30303 Phone: 404-652-6493 Quality: 912-280-6839



Technical Data Sheet

Golden Isles Fluff Grade 4800

Pulping Process	Kraft
Bleaching Process	ECF
Wood Species	Southern Pine
Typical Properties	
Average Fiber Length	
Length Weighted (mm)	2.7
Weight Weighted (mm)	3.4
Basis Weight (g/m ²)	765
Caliper (mm)	1.27
Density (g/cc)	0.57
Mullen (kPa)	1380
Moisture (%)	6.0
Extractives (%)	0.03
Brightness (ISO)	87.0
Kamas Energy (kWh/ton)	32
Fiberization (%)	95.0
Specific Absorption (sec/g)	< 0.75
Specific Capacity (g/g)	10.5
Wet Bulk (cc/g)	8.4
Packaging	
Roll Width (cm)	25 - 152
Roll Diameter (cm)	115 - 152
Core Diameter (cm)	7.6
` '	

Applications: Golden Isles Fluff is a high-performance fluff that provides superior absorbency and pad integrity, especially important for thinner absorbent products. This grade is widely used in baby diapers, adult incontinence and feminine hygiene products.